



# S-40

## TECHNICAL DATA SHEET

### S-40 Roofing Underlayment

#### DESCRIPTION:

Product No. S-40 Roofing Underlayment with its advanced engineering is highly recommended for mechanically attached, coated woven synthetic roofing underlayment for sloped roofs. Product No. S-40 is specifically manufactured to replace the #30 felt.

#### FEATURES AND BENEFITS:

- 1 year UV protection
- Water repellent, non-absorbent
- 11 mil thickness
- Works best for use under Metal, Shake and Shingle Roofing
- Does not wrinkle, crack or become stiff in colder temperatures for smooth and easy installation
- Product No. S-40 will not dry out or leach oil in high heat environments as organically saturated felts do
- 5 times lighter and 25 times stronger than 30# felt
- 40 year limited warranty
- Class A Fire ASTM E 108 - Meets & exceeds ASTM D4869 and D226
- Synthetic construction impervious to mold growth
- Product No. S-40 4 ply underlayment (3 ply cross-woven coated polypropylene with a layer of non-woven polypropylene)
- Strong and durable polymer construction
- 100% Recyclable
- Temperature performance range -40°F to 260°F (-40°C to 126°C)

#### CERTIFICATIONS:



#### PRODUCT INFORMATION:

- Width: 48 Inches
- Length: 250'
- Weight: 29 lbs
- Rolls Size: 10 sq

#### LIMITED WARRANTY AND DISCLAIMER:

To the best of our knowledge, the technical data contained herein is true and accurate at the date of issuance and is subject to change without prior notice. User must contact TRC to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. Liability, if any, is limited to replacement of product unless installed by an approved contractor in accordance with TRC warranty procedures and program. For limited manufacturer's warranty and disclaimer information, visit our website at: [www.rubberized.com](http://www.rubberized.com).

#### CERTIFICATION TESTING:

TEST & STANDARD	TYPICAL VALUE
Class A Fire ASTM E108	PASS
Nail Sealability Modified ASTM D1970	PASS
Water Permeability ASTM E96	No Dripping
Water Transmission ASTM D4869	PASS
Tear Strength ASTM D4533	MD 18 lbs/CD 21 lbs
Tensile Strength ASTM D751	MD 85 lbs/CD 84 lbs
Elongation ASTM D751	MD 18%/CD 18%
Weight per Square ASTM D5261	2.9 lbs/1.32 kgs