

PRODUCT NO.

910



- ✓ 100% SILICONE DESIGNED FOR UNMATCHED DURABILITY AND LONGEVITY
- ✓ HIGH VISCOSITY FOR APPLICATIONS ON VERTICAL SURFACES
- ✓ REPAIR OR SEAL PENETRATIONS THAT HAVE EXISTING SILICONE COATING

# 910

# 100% SILICONE FLASHING SEALANT

## DESCRIPTION:

Product No. 910-Flashing Sealant is a high performance one-part, moisture curing, and room temperature vulcanizing (RTV) 100% silicone flashing sealant combined with reinforcing materials to provide strong seal-ability around roof fasteners, transitions and penetrations.

Product No. 910-Flashing Sealant has ultra-high strength and remains very durable. It will maintain its integrity on fasteners and penetrations with movement.

Product No. 910-Flashing Sealant exhibits excellent unprimed adhesion to concrete, metals and most other roofing substrates, provided they are clean, dry and free of dust and frost.

Product No. 910-Flashing Sealant is unaffected by sunlight (ultra-violet rays), ozone, temperature extremes, rain and snow. It has a long service life, and it was designed to perform between -60°C to 200°C (-76°F to 392°F).

## TYPICAL USES:

- Repair material for metal and SPF roofs
- Seal fasteners, seams and details on low and semi-steep sloped roofs
- Pipe penetrations through roof decks in metal flashings
- Concrete, metal and most construction substrates
- Mold and mildew resistance

## SURFACE PREPARATION:

All penetrations must be clean, dry and free of contaminants before Product No. 910-Flashing Sealant is applied. Dust and loose particles must be blown out of the joint with oil-free compressed air, moving only in one direction. An oily surface may reduce adhesion.

## APPLICATION:

*Always test adhesion before applying to different substrates.*

Product No. 910-Flashing Sealant is ready-to-use and requires no mixing or additives. Apply Product No. 910-Flashing Sealant to roofing substrate, fastener or penetration using appropriate caulking gun, brush, trowel, joint knife or plastic spatula to achieve a uniform membrane over the transition surfaces. Top coat with Product No. 990 Forever-Coat Silicone Roof coating when dry to touch.

Product No. 910-Flashing Sealant can be applied in a single coat. Spread uncured Product No. 910-Flashing Sealant to extend a minimum of 4" (100 mm) over the surface of the roof. Regularly monitor wet film thickness during application to ensure adequate uniform coverage. Coverage may vary depending on application technique and nature of substrate. Curing begins as soon as the sealant comes in contact with air. Application at temperatures below 4°C (40°F) will slow curing, while increased levels of humidity will aid curing. Tooling should be done before skin-over takes place. Remove wet material from application/spreading tool with a rag before the material cures. Carefully use appropriate cleaning agent, such as citrus solvent or odorless mineral spirits, to remove cured material from tools. For best results, follow precautions on packaging.

## STORAGE:

Product No. 910-Flashing Sealant, when stored in original, unopened container in dry, shaded conditions, away from sources of heat or ignition, and stored below 32°C (90°F), has a shelf life of 12 months from date of manufacture.

## PACKAGING:

Product No. 910-Flashing Sealant is available in 18.9L (5 US gallon) pails.

## PRODUCT CHARACTERISTICS AND PRACTICAL INFORMATION

Type	100% silicone, one-part RTV
Appearance	Smooth, thick paste
<b>Temperature Range‡</b>	
Application Temperature Range	Ambient to 50°C (120°F)
Useable Temperature Range	-60°C a 200°C (-76°F a 392°F)
<b>Drying Time*</b>	
Tooling/Skin-Over Time	85 minutes
Cure Time	24 hours
Full Physical Characteristics	7 days

## PHYSICAL PROPERTIES

*(Typical properties - values not to be used as specifications)*

<b>Uncured</b>	
Specific Gravity	1.28
Slump/Sag	Non-flow
Cure System	Neutral (Oxime), Moisture Cure
<b>Cured At Standard Conditions* for 7 Days</b>	
Durometer Hardness (ASTM D2240, Shore A)	43 points
Tensile Strength (ASTM D412)	160 psi (11 kg/cm <sup>2</sup> )
Elongation at Break (ASTM D412)	67%
Tear Resistance (ASTM D624, Die B)	27 ppi (4.7 kN/m)

*‡Please consult TRC for suitability for application at lower temperatures  
\*At standard conditions 77oF (25oC) and 50% relative humidity*

## COLORS

Product No. 910-Flashing Sealant is available in White.

## LIMITED WARRANTY AND DISCLAIMER:

Tucson Rubberized Coatings, Inc. warrants that its products will meet its specifications. TRC shall in no event be liable for incidental or consequential damages. Except as expressly stipulated, TRC 's liability, expressed or implied, is limited to the stated selling price of any defective goods. Data is subject to change without notice and it is therefore recommended that this information not be used for specification writing. For additional information on specific applications, contact Tucson Rubberized Coatings, Inc.